

## Cafco FENDOLITE® MII Product Data Sheet

### Non-reactive fire protective coating



[www.promatmiddleeast.com](http://www.promatmiddleeast.com) | [www.promat-india.com](http://www.promat-india.com)





## General description

Cafco FENDOLITE® MII is a spray applied, single package factory controlled premix, based on vermiculite and Portland cement.

Cafco FENDOLITE® MII produces a monolithic coating able to withstand thermal shocks experienced typically in a high intensity hydrocarbon fire. Concrete structures in particular, will be protected from explosive spalling when protected using Cafco FENDOLITE® MII.

Although low in density, thus significantly reducing dead load, Cafco FENDOLITE® MII is highly durable and will not crack or spall under mechanical impact.

Cafco FENDOLITE® MII is used for application to construction elements such as concrete or individual steel sections, particularly where off-site application is required. It is suitable for exterior use on structures and vessels in the oil, gas, petrochemical and power industries, and for refurbishment or upgrading of existing tunnel structures.

## Fields of application

The product is suitable for internal and external use for fire protection of:

- concrete structures
- steel structures
- vessels in the oil and gas, petrochemical and power industries
- tunnel structures

## System advantages / customer benefits

- structures protected with Cafco FENDOLITE® MII can provide fire resistance for up to 240 minutes
- does not release toxic or hazardous fumes
- the surface may either be spray textured, roller or float finished

## Packaging

- 20 kg plastic bags
- 50 bags/pallet

Subject to change.

## Storage requirements

- store in cool and dry conditions
- protect from moisture
- shelf life of original sealed containers at least 12 months
- once opened, bags should be finished swiftly

## Safety instructions

- Keep out of reach of children.
- Avoid contact with food or beverages
- Please refer to the safety data sheet for additional advice

## Properties and performance

Colour and finish	Off-white with a monolithic spray texture
Alkalinity	12.0 - 12.5 pH
Sound absorption	0.35 Noise Reduction Coefficient (NRC)
Cure	By hydraulic set
Initial set	2 to 6 hours at 20°C and 50% RH
Minimum practical thickness	8mm when unreinforced, 15mm when reinforced
Theoretical coverage	62m <sup>2</sup> /tonne at 25mm thickness
Density	775kg/m <sup>3</sup> ± 15% in accordance with ASTM E605
Durometer hardness	40 (Shore D) in accordance with ASTM D2240
Compressive strength	4531kPa (accordance with ASTM E761)
Combustibility	Non-combustible in accordance with ASTM E136 and BS 476: Part 4
Surface burning	0 flame spread, 0 smoke developed
Deflection effect	No cracks or delamination or spalling
Impact resistance	No cracking, delamination or spalling in accordance with ASTM E760
Thermal conductivity	1.5 BTU in/hour ft <sup>2</sup> (0.216W/mK) at 24°C
Corrosion resistance	Does not promote corrosion of steel.
Fungal resistance	0 rating - no fungus growth in accordance with ASTM G21

## Test certificate / approval

Cafco FENDOLITE® MII is assessed by Warrington Certification (Certificate CF 5570) and UL-listing. Loadbearing steel, loadbearing concrete elements and loadbearing flat concrete profiled sheet composite elements are tested in accordance with applicable British standards (BS) and US standards (ASTM). Depending on the applied layer thickness and area of application, fire resistance 30 minutes to 240 minutes can be achieved.

## Top Coating

Cafco® TOPCOAT 200 may be used as protection from frequent wash down, long term chemical spills, or for improved resistance to fungal, algal and bacterial growth.





## CONTACT US

Contact us for your requirements. We look forward to advising you on your projects.

### Middle East

#### Promat Fire Protection LLC

Plot 597 - 921, Dubai Investment Park 2, Dubai, United Arab Emirates  
T +971 4 885 3070 | E [promatmiddleeast@etexgroup.com](mailto:promatmiddleeast@etexgroup.com)

### India

#### Promat Fire & Insulation Private Limited

Unit No. 605, 6th Floor, Tower B, Global Business Park, Mehrauli Gurgaon Road, Sector 26, Gurgaon, 122 002 Haryana, India  
T +91 (0) 124 434 6865 | E [promatindia@etexgroup.com](mailto:promatindia@etexgroup.com)

### Head Office

#### Promat International N.V.

Bormstraat 24, 2830 Tiselt, Belgium  
T +32 15 718 100 | E [info@promat-international.com](mailto:info@promat-international.com)